JC6-7


6V 7Ah



JAPCELL JC6-7 is an AGM battery. It is designed for stand-by applications such as Security and Alarm systems, Emergency lights, Electronic scales.

SPECIFICATION

Nominal Voltage	6V (3 cells in series)
Rated Capacity	7.0Ah (C_{20},1.75V/cell)
Dimensions(mm)	151Length x 34.5Width x 94.5mm(max.100.5)Height
Nominal Capacity @25℃ (Ah)	20 Hour rate (0.354A to 5.25 volts) 7.08Ah 10 Hour rate (0.676A to 5.25 volts) 6.76Ah 5 Hour rate (1.208A to 5.25 volts) 6.04Ah 1 Hour rate (4.550A to 4.80 volts) 4.55Ah 15 min rate (13.48A to 4.80 volts) 3.37Ah
Approx. Weight	1.0 kg
Terminal	F1
Max.Discharge Current	105A @25℃ (5s)
Internal Resistance	13mΩ @25℃
Floating Design Life	5 years @25℃
Ambient Temperature	Charge：-15℃~50℃ Discharge：-20℃~60℃ Storage：-20℃~50℃
Container Material	A.B.S, UL94-HB, UL94-V0, Optional
Self Discharge	VRLA batteries can be stored for more than 6 months at 25℃. Self-Discharge ratio less than 3% per month at 25℃. Please charge batteries before using.



CONSTANT CURRENT DISCHARGE CHARACTERISTICS (A), (25℃)

F.V/Time	5min	10min	15min	30min	60min	2H	3H	5H	8H	10H	20H
1.60V/cell	27.62	18.10	13.48	7.175	4.550	2.563	1.831	1.235	0.818	0.700	0.375
1.70V/cell	25.06	16.77	12.71	6.965	4.449	2.524	1.785	1.217	0.805	0.683	0.361
1.75V/cell	22.51	15.72	12.01	6.755	4.393	2.503	1.768	1.208	0.798	0.676	0.354
1.80V/cell	20.20	14.70	11.31	6.545	4.330	2.482	1.747	1.194	0.788	0.665	0.340

JAPCELL®


JC6-7

6V 7Ah


CONSTANT WATTAGE DISCHARGE CHARACTERISTICS (WATT), (25℃)

F.V/Time	5min	10min	15min	30min	60min	2H	3H	5H	8H	10H	20H
1.60V/cell	49.94	33.02	24.82	13.69	9.024	5.084	3.649	2.463	1.631	1.398	0.749
1.70V/cell	46.15	31.15	23.82	13.41	8.860	5.026	3.564	2.429	1.607	1.365	0.724
1.75V/cell	42.01	29.73	22.71	13.12	8.756	4.988	3.532	2.413	1.595	1.352	0.710
1.80V/cell	38.03	28.05	21.57	12.82	8.637	4.951	3.493	2.387	1.575	1.331	0.682


Charge Characteristics Curve




Discharge Characteristics Curve



Cycle service life in relation to depth of discharge



Capacity Storage Characteristics



CAPACITY FACTORS WITH DIFFERENT TEMPERATURE

Battery type		-20℃	-10℃	0℃	5℃	10℃	20℃	25℃	30℃	40℃	45℃
GEL Battery	**6V & 12V**	50%	70%	83%	85%	90%	98%	100%	102%	104%	105%
	2V	60%	75%	85%	88%	92%	99%	100%	103%	105%	106%
AGM Battery	**6V & 12V**	46%	66%	76%	83%	90%	98%	100%	103%	107%	109%
	2V	55%	70%	80%	85%	92%	99%	100%	104%	108%	110%

CHARGING METHOD

☼ Charging Procedure：

Application	Charging method	Charge voltage at 25℃	Temperature compensation coefficient of charging voltage	Max.charging current	Temperature
For standby power source	Constant voltage charging (With current restriction)	2.25~2.30 V/cell	-3mV/℃/cell	0.2CA	-15~50℃
For cycle service		2.45~2.50 V/cell	-4mV/℃/cell	0.3CA	

☼ Charge the batteries at least once every six months, if they are stored at 25℃.

Constant Voltage: -0.2C×2h+2.45-2.50V/cell×24h, Max. Current 0.25CA

Constant Current: -0.2C×2h+0.1C×12h

Fast: -0.2C×2h+0.3C×4h